

# OBEX™ TILE: CUT

Entrance Flooring

## Construction

Tufted, Cut Pile

## Tile Size

50 cm x 50 cm (19.7" x 19.7")

## Yarn Type

Milliken-Certified WearOn® Nylon and Monofilament

## Dye Method

PrintWorks™ Precision Dye

## Tufted Face Weight

28 oz/yd<sup>2</sup> (949 g/m<sup>2</sup>)

## Gauge

5/32

## Stitches Per Inch

5.6

## Tufts

35.8/in<sup>2</sup> (554/100 cm<sup>2</sup>)

## Finished Pile Height

0.182" (4.62 mm)

## Average Density (Finished)

5,281

## Standard Backing

PVC-Free WellBAC® Comfort Plus Cushion

Available with TractionBack®

## Recycled Content by Total Weight

36.2% Pre-Consumer,  
0.0% Post-Consumer

## Embodied Carbon

21.15 (kg CO<sub>2</sub>e)/m<sup>2</sup>

## Nominal Total Thickness

0.50" (12.7 mm)

## Nominal Total Weight

130.0 oz/yd<sup>2</sup> (4,407 g/m<sup>2</sup>)

## Flammability (Radiant Panel

ASTM-E-648)

≥ 0.45 (Class I)

## Smoke Density (NFPA-258-T or

ASTM-E-662)

≤ 450

## Methenamine Pill Test (CPSC FF-1-70

or ASTM D 2859

Self-Extinguishing

## Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

## Crocking (AATCC 165)

≥ 4.0 Wet or Dry

## Static Electricity (AATCC-134) 20%

R.H., 70° F.

≤ 3.5 KV, Permanent Conductive Fiber

## Recommended Maintenance

Daily Vacuum, Deep Clean via Hot Water Extraction

## Indoor Air Quality—CRI Green Label Plus™

GLP0793, Carpet Category 5Y

## Recommended Installation Method(s)

Monolithic, Quarter-Turn, Ashlar

## Pieces Per Box

12 Tiles, 32.29 ft<sup>2</sup> (3.0 m<sup>2</sup>)

## Installation Zone Application

Zone 2 or Zone 3

## WARRANTIES

Lifetime Face Fiber Wear

Lifetime Antistatic

Lifetime Floor Compatibility

Lifetime Color Pattern Permanency

Lifetime Floor Release

Lifetime Cushion Resiliency

Lifetime Moisture Resistance

Lifetime Delamination of Backing

Lifetime Staining/Soiling (StainSmart®)

Lifetime Dimensional Stability

Lifetime Tuft Bind

Lifetime Edge Ravel



This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.