

IDENTITY LOGO MATS Textile logo mats for entrance flooring solutions

Product description	Tufted cut pile manufactured with twisted and heat set BCF Polyamide 6 Econyl fibres on nitrile rubber backing			
	Fire resistance	Cfl-s1		
	Total thickness	8mm		
	Total Weight	2800g/m ² (+/- 5%)		
Yarn	Composition	100% Polyamide 6 Econyl BCF, twisted and heatset multifilaments		
Primary Backing	Composition and construction	n Polyester nonwoven		
Dila	Construction	Cut pilo		
Pile	Construction	Cut pile		
	Tuft method	Straight tufted		
	Pile height	8.0mm		
	Stitch rate	8.5spi		
	Total fabric weight	940g/m ²		
Textile Colour Fastness	Dyeing Method	High definition digital dye injection technology		
	Light	5	(ISO 105-B02)	
	Rubbing	4-5	(ISO 105-X12)	
	Water	5 / 4-5	(ISO 105-E01)	
	Seawater	5 / 4-5	(ISO 105-E02)	
	Organic Solvents	4-5	(ISO 105-D02)	
Secondary Backing	Composition	100% Nitrile Rubber		
	Mass		1650g/m ² (body of mat)	
	Backing thickness	1.3mm		
	Border thickness	2.6mm		
	Border width	20mm		
	Phthalates	NO Ortho-phthalates in this rubber		
Performance Testing	Electrical Resistance	3.1x10 ¹² / 1.2x10 ¹¹	(ISO 10965)	
	Personal Charging	-1.5kV	(ISO 6356)	
	Flammability	Cfl-s1	(EN ISO 13501)	
	Slip Resistance	0.49 DS	(EN 13893)	
	Changes in Appearance	31/32	(ISO 10361)	
Size and Weights (approx.)	85x60cm	115x200cm	200x200cm	
	85x120cm	115x240cm	200x300cm	
	85x150cm	115x300cm	200x400cm	
	85x300cm	150x250cm	200x500cm	
	115x180cm	150x300cm		
ADA / BS 8300 / ISO 21542 Co	moliant	Yes		
LEED® Point Contributor		Yes		
ISO Manufacturing Certification		ISO 9001		
ISO Environmental Certification		ISO 14001		
Origin		EU		
Warranty		Please refer to our writt	en warranty	



Please Note: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/ labelling /processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labelling, marketing, etc. All sales are exclusively subject to our standard terms of sales posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.